

Description: Masking Tapes

No.	Product	Color	Adhesive	Thickness (micron)	Peel Adhesion at 180°(N/25mm)	Temperature Resistance(°C)
OT-322HW_OT-322HB	Masking Tape General Purpose	various	rubber	155±10	7.0±0.5	60°C

TEST METHOD:

THICKNESS: ASTM-D5199

TACK¹: PSTC-6

TACK²: J.DOW.METHODS

PEEL: 180° ADEHESION TO STEEL, PSTC-1

HOLDING POWER: SHEAR TO STEEL, 1" x 1" x 1KG, 178°, PSTC-7

TENSILE & ELONGATION: PSTC-31

TESTING WERE CARRIED OUT IN 23±2°C AND 65±5%RH.

color swatch



Color #

OT-322HW

OT-322HY

OT -322HR

OT -322HO

OT -322HG

OT -322HE

OT -322HB



An American owned manufacturing in Mainland China

Designer / Manufacturer of equipments with accessories for adhesive tape industries and supply Adhesive Tapes

Head Office: P.O. Box 1547 • 1000 Corporate Center Drive, Monterey Park, California 91754, USA

<http://www.otape.com> • email: sales@otape.com • Toll Free: 1-877-302-8981 • Fax: 1-877-302-8981

Office in China: 2103, No. 7, Lane 89, An-Shun Road, Chang Ning District, Shanghai 200052, China

Tel: +86-21-52306651 • Fax: +86-21-52306651 • 24 Hour Hotline: +86-13915497733 • email: info@otape.com

Plant 1: 6, Shang Yu Road, Industrial Park District, Shu Yang, Jiangsu 223600, China

Plant 2: 8, Xinyi Road. Economic Development Zone, Jingjiang, Jiangsu 214500, China

Distribution in Sri Lanka: 164 Puttalam Road, Kurunegala, Sri Lanka

Description: Masking Tapes

No.	Product	Color	Adhesive	Thickness (micron)	Peel Adhesion at 180°(N/25mm)	Temperature Resistance (°C)
OT-309H_OT326H	Masking Tape High Temperature	white	rubber	150±10	6.5±0.5	80°C/30 minutes
		yellow	rubber	150±10	6.5±0.5	110°C/1 hours
		white	rubber	150±10	4.5±0.5	130°C/1 hours

color swatch



Color# OT-309H OT-358H OT-326H



Description: Masking Tapes

No.	Product	Color	Thickness (micron)	Adhesive	Confining Force	Peel Adhesion at 180°(N/25mm)	Temperature Resistance (°C)
OT-7288H	Masking Tape	orange	95±5	Water base	> 3 hour	4.0	130°C/2 hours

color swatch



Color# OT-7288H



TEST METHOD:

THICKNESS: ASTM-D5199

TACK¹: PSTC-6

TACK²: J.DOW.METHODS

PEEL: 180° ADEHESION TO STEEL, PSTC-1

HOLDING POWER: SHEAR TO STEEL, 1" x 1" x 1KG, 178°, PSTC-7

TENSILE & ELONGATION: PSTC-31

TESTING WERE CARRIED OUT IN 23±2°C AND 65±5%RH.

An American owned manufacturing in Mainland China

Designer / Manufacturer of equipments with accessories for adhesive tape industries and supply Adhesive Tapes

Head Office: P.O. Box 1547 • 1000 Corporate Center Drive, Monterey Park, California 91754, USA

<http://www.otape.com> • email: sales@otape.com • Toll Free: 1-877-302-8981 • Fax: 1-877-302-8981

Office in China: 2103, No. 7, Lane 89, An-Shun Road, Chang Ning District, Shanghai 200052, China

Tel: +86-21-52306651 • Fax: +86-21-52306651 • 24 Hour Hotline: +86-13915497733 • email: info@otape.com

Plant 1: 6, Shang Yu Road, Industrial Park District, Shu Yang, Jiangsu 223600, China

Plant 2: 8, Xinyi Road. Economic Development Zone, Jingjiang, Jiangsu 214500, China

Distribution in Sri Lanka: 164 Puttalam Road, Kurunegala, Sri Lanka